

CLAIMS

[Handwritten signature]

1. A paper for ink jet and electrophotographic recording which comprises a support having a cationic resin adhered thereto in a dry adhering amount of 0.5-
5 2.0 g/m² and which has a surface resistivity of $1.0 \times 10^9 - 9.9 \times 10^{13} \Omega$.
2. A paper for ink jet and electrophotographic recording according to claim 1, wherein the cationic resin has a cation equivalent of 3-8 meq/g measured by
10 colloidal titration method.
3. A paper for ink jet and electrophotographic recording according to claim 1, wherein the support has a neutral rosin sizing agent or an alkenyl succinic anhydride as an internal sizing agent.
- 15 4. A paper for ink jet and electrophotographic recording according to claim 1, wherein the support contains a waste paper pulp.